

Properties	Ethyl Acrylate Content	MFR	Density	Melting Point	Softening Point	Brittleness (F50)	Tensile Modulus	Tensile Strength	Ultimate Elongation	Durometer Hardness		JHOSPA PL No.	Application
					Vicat					Shore A	Shore D		
Unit	%	g/10min	g/cm ³	°C	°C	°C	MPa	MPa	%	HDA	HDD		
Products													
NUC-6220	7	4	0.93	98	70	<-75	80	14	>650	95	42	[A]EZa-0278	Coating
DPDJ-6182	15	1.5	0.93	97	65	<-75	50	>15	>650	92	36	[A]EZa-15573	Injection • Blow
DPDJ-6169	18	6	0.93	95	55	<-75	40	>12	>650	82	34	[B]NJ-1693	Injection • Blending
NUC-6170	18	6	0.93	95	56	<-75	39	>12	>650	88	34	[A]EZa-3564	Coating
DPDJ-9169	20	20	0.93	92	47	<-75	35	>9	>650	86	32	[B]NJ-1693	Blending
NUC-6510	23	0.5	0.93	94	58	<-75	32	>14	>650	82	36	[A]EZa-16370	Extrusion • Blending
NUC-6520	24	1.5	0.93	93	54	<-75	26	>9	>600	87	33	[A]EZa-16370	Extrusion • Blending
NUC-6570	25	20	0.94	90	43	<-75	25	>7	>650	78	28	[B]NL-1693	Hotmelt • Blending
NUC-6070	25	250	0.94	89	30	<-55	21	3	220	74	24	[B]NJ-14275	Hotmelt • Blending
NUC-6940	35	20	0.95	83	43	<-75	10	>4	>650	70	19	[B]NL-14572	Hotmelt • Blending

Note • The values are dependent upon using the testing method as indicated and are offered herein as a guide in the use of compound.