

Properties	Vinyl Acetate Content	MFR	Density	Melting Point	Softening Point	Brittleness (F50)	Tensile Modulus	Tensile Strength	Ultimate Elongation	Durometer Hardness		JHOSPA PL No.	Application
					Vicat					Shore A	Shore D		
Unit	%	g/10min	g/cm ³	°C	°C	°C	MPa	MPa	%	HDA	HDD		
Grade													
NUC-3660	6	5.5	0.93	103	79	< -75	141	>14	600	94	49	[A]EZa-15615-L	Injection
NUC-8450	14	1.3	0.92	92	68	< -75	57	>13	>600	95	40	[A]EZa-3525-L	Extrusion
NUC-3830	15	12	0.94	86	59	< -75	50	17	800	90	33	[A]EZa-14306-L	Injection • Coating • Hotmelt
NUC-3461	20	14	0.94	82	50	< -75	34	>10	>650	86	34	[A]EWa-2365-L	Extrusion
NUC-3888	21	1.8	0.94	75	56	< -75	-	12	650	-	30	[A]EWa-2365-L	Extrusion
NUC-3195	24	5.0	0.95	79	49	< -75	28	>13	>650	86	33	[A]EZa-0279	Injection • Extrusion
DQDJ-3269	28	22	0.95	73	47	< -75	17	7	>600	82	29	[A]EWa-15501-L	Injection • Hotmelt

Note • The values are dependent upon using the testing method as indicated and are offered herein as a guide in the use of compound.